


Test Report

Issue Date: 2020-09-10 Intertek Report No. : 200827008SHF-004
 Test Date: 2020-08-27 - 2020-09-10
 Applicant: Ekologix Australia Pty Ltd
 Address: Unit 1, 20-26 Sabre Drive, Port Melbourne, Victoria, Australia 3207
 Test Type : Performance test, samples provided by the applicant.
 Document Control Number: LFT-APAC-SHF-OP-10k(May 1, 2020)



Product Information

Product Name	Designer Series, Designer Series Edge Boards Flame Fighter BAL29 WPC Co-Extrusion Decking	Brand	Ekodeck
Sample Description	Good Condition	Sample Amount	8pcs
		Received Date	2020-08-26
Sample ID	Model	Specification	
S200827008SHF.002, 004	BR6(CC/RR)	137*23mm	

Test Items, Method and Results:

Test Item: Creep recovery
 Test Method: ASTM D7032-17 Section 5.4
 Conditioning: Condition the test specimens at (23±2°C) and (50±5)% RH for not less than 40 h
 Test Span: 450mm
 Applied Load: 100psf

Test Result	Requirement	Verdict
Creep recovery: 84%	≥75%	Pass

Appendix A: Sample Received Photo



Report Authorized


 Name: Flora Fan
 Title: Reviewer


 Name: Mason Wang
 Title: Project Engineer

