


Test Report

Test Date(s): 2020-09-14 - 2020-09-24
 Intertek Report No: 200914002SHF-001
 Issue Date: 2020-09-24
 Applicant: Ekologix Australia Pty Ltd
 Address: Unit 1, 20-26 Sabre Drive, Port Melbourne, Victoria, Australia 3207
 Test Type: Performance test, samples provided by the applicant.
 Document Control Number: LFT-APAC-SHF-OP-10k(May 1, 2020)



Product Information

Product Name	Designer Series, Designer Series Edge Boards Flame Fighter BAL29 WPC Co-Extrusion Decking	Brand	Ekodeck
Sample Description	Good Condition	Sample Amount	2pcs
		Received Date	2020-09-11
Sample ID	Model	Specification	
S200914002SHF.001	BR6	137*23mm	

Test Items, Method and Results:

Test Item: Hardness
 Test Method: ASTM D1037-12 section 17
 Indenter: a "ball" 0.444 in. (11.3 mm) in diameter
 Test Speed: 6 mm/min

Results:

Test Item	Results
Hardness	10.78KN

Appendix A: Sample Received Photo



Front View




Back View



Section View

Report Authorized



 Name: Flora Fan Name: Mason Wang
 Title: Reviewer Title: Project Engineer